

DuPont™ Kalrez® 3065

Technical Information — Rev. 3, July 2010

Product Description

DuPont™ Kalrez® 3065 is a highly-filled product containing carbon black and fiber reinforcement, designed to function without extrusion under extreme pressure. It has good all round chemical resistance and excellent resistance to sour oil and amines. Kalrez® 3065 has an upper service temperature of 288 °C (550 °F).

The mechanical properties and chemical resistance of Kalrez® 3065 make it the best choice for many oil and gas well applications. In these applications it is normally used in the form of V-rings and other custom parts rather than O-rings.

The physical properties of Kalrez® 3065 are as follows:

Typical Physical Properties¹

Hardness ² , Shore A (pellets) ± 5	90
100% Modulus ³ , MPa (psi)	N/A ⁷
Tensile Strength at Break ³ , MPa (psi)	24.10 (3495)
Elongation at Break ³ , %	30
Compression Set ⁴ , 70 hr at 204 °C (400 °F), %	N/A
Brittle Point ⁵ , °C	-23
Maximum continuous service temperature ⁶ , °C (°F)	288 (550)

¹ Not to be used for specifications

² ASTM D2240

³ ASTM D412, 500 mm/min (20/μm)

⁴ ASTM D395 B, pellets

⁵ ASTM D746

⁶ DuPont Performance Polymers proprietary test method

⁷ N/A = Not applicable



The miracles of science™

AUTHORIZED DISTRIBUTOR

DuPont™ Kalrez®
PERFLUOROELASTOMER PARTS

◀ DU PONT ▶

"Ask for the Seal You Can Trust"

VARISCO & CO

Chemical Resistance	DuPont™ Kalrez® 3065
Aromatic/Aliphatic oils	+++
Acids	++
Alkalis	++
Alcohols	+++
Aldehydes	+++
Amines	+++
Ethers	+++
Esters	+++
Ketones	+++
Steam/Hot Water	++
Strong Oxidizers	0
Ethylene/Propylene Oxide	--

+++ = Excellent ++ = Very Good + = Good 0 = Marginal -- = Poor --- = Not Recommended

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America 800-222-8377	Latin America +0800 17 17 15	Europe, Middle East, Africa +41 22 717 51 11
Greater China +86-400-8851-888	ASEAN +65-6586-3688	Japan +81-3-5521-8484

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee favorable results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications and DuPont CAUTION Regarding Medical Application.

Copyright © 2014 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(03/13) Reference No. KZE-A11073-00-C0518

