

DuPont™ Kalrez® Spectrum™ 6380

Technical Information — Rev. 3, July 2010

Product Description

DuPont™ Kalrez® Spectrum™ 6380 perfluoroelastomers parts are a non-black product specifically developed for chemical processes involving hot, aggressive amines. In addition, it has excellent overall chemical resistance (see chart below). This cream colored product is easily identifiable when selecting an O-ring material for harsh chemical plant services. This material has excellent mechanical properties and is a top choice for both static and dynamic sealing applications. A maximum continuous service temperature of 225 °C is suggested while short-term excursions to higher temperatures are permissible.

For more information on Kalrez® Spectrum™ 6380, or to see if it might be right for your difficult sealing applications in amines and other aggressive chemical streams, please contact DuPont.

Typical Physical Properties¹

Hardness, Shore A ² ±5	80
100% Modulus ³ , MPa (psi)	6.89 (1000)
Tensile Strength at Break ³ , MPa (psi)	15.86 (2300)
Elongation at Break ³ , %	160
Compression Set ⁴ , 70 hr at 204 °C, %	40

¹ Not to be used for specification purposes

² ASTM D2240

³ ASTM D412, 500 mm/min (20 in/min)

⁴ ASTM D395B, size 214 O-ring

Chemical Resistance (672 hour exposure)

Material Compound	Temperature, °C	DuPont™ Kalrez® Spectrum™ 6380 Rating
Chemical Resistance to:		
Acetic Acid	100	A
Nitric Acid (fuming)	60	A
Diethyl Amine	50	A
Monoethanolamine	150	B
Ethylene Diamine	90	A
Butyraldehyde	70	A
Methanol	100	A
Toluene	100	A
Water	225	A

Rating: A: < 10% volume change and minimal effect on elastomer properties

B: 10–20% volume increase and slight effect on elastomer properties

C: > 20% volume increase and significant effect on elastomer properties

X: Elastomer not recommended for this service



The miracles of science™

AUTHORIZED DISTRIBUTOR

DuPont™ Kalrez®
PERFLUOROELASTOMER PARTS

◀ DU PONT ▶

"Ask for the Seal You Can Trust"

VARISCO & CO

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee favorable results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications and DuPont CAUTION Regarding Medical Application.

Copyright © 2014 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(03/13) Reference No. KZE-A11073-00-C0518



The miracles of science™

AUTHORIZED DISTRIBUTOR

DuPont™ Kalrez® <DUPONT>
PERFLUOROELASTOMER PARTS

"Ask for the Seal You Can Trust"

VARISCO & CO