

DuPont™ Kalrez® Spectrum™ 0040

For Low-Temperature Applications

Technical Information — Rev. 2, June 2011

Product Description

Kalrez® Spectrum™ 0040 perfluoroelastomer parts are specifically designed for low-temperature environments where significant chemical resistance is required. Proprietary polymer and cure technology promotes low-temperature sealing performance (-42°C) of Kalrez® Spectrum™ 0040 parts to temperatures typically unattainable for perfluoroelastomer parts. Kalrez® Spectrum™ 0040 is an excellent choice in applications such as couplings for the chemical transportation industry, or for other applications where chemical resistance and elasticity are required in some of the coldest environments. The volume swell for Kalrez® Spectrum™ 0040 is approximately 10% when exposed to nitric acid at 110°C for 168 hours. Compression set resistance is similar to that of our broad chemically-resistant product, Kalrez® Spectrum™ 6375.

Typical Physical Properties¹

Color	Black
Hardness, Durometer Shore A ²	70
100% Modulus ³ , MPa (psi)	5.17 (750)
Tensile Strength at Break ³ , MPa (psi)	8.96 (1300)
Elongation at Break ³ , %	170
Compression Set ⁴ , %	
70 hrs. at 200°C (392°F)	41
336 hrs. at 200°C (392°F)	57
672 hrs. at 200°C (392°F)	62
Upper Service Temperature, °C (°F) ⁵	220 (428)
Lower Service Temperature, °C (°F) ⁵	-42 (-43.6)
Tg °C (°F) ⁵	-27 (-16.6)
Tr10 °C (°F) ⁶	-17(1.4)
<u>Volume Swell (% Change)⁷, 168 hours</u>	
Nitric Acid, 110°C (230°F)	10
Ethylenediamine, 194°F (90°C)	19

¹Not to be used for specification purposes

²ASTM D2240 (pellet test specimens)

³ASTM D412 500mm/min (dumbbell test specimens)

⁴ASTM D395B (AS568 K214 O-ring test specimens)

⁵DuPont proprietary test method

⁶ASTM D1329 (slab test specimens)

⁷ASTM D471 (AS568 K214 O-ring test specimens)



The miracles of science™

AUTHORIZED DISTRIBUTOR

DuPont™ Kalrez®
PERFLUOROELASTOMER PARTS

"Ask for the Seal You Can Trust"

VARISCO & CO

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee favorable results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications and DuPont CAUTION Regarding Medical Application.

Copyright © 2014 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(03/13) Reference No. KZE-A11073-00-C0518



The miracles of science™

AUTHORIZED DISTRIBUTOR

DuPont™ Kalrez® <DUPONT>
PERFLUOROELASTOMER PARTS

"Ask for the Seal You Can Trust"

VARISCO & CO