



# Kalrez® 8775

## PERFLUOROELASTOMER PARTS

Kalrez® 8775 is a black product for semiconductor applications that offers excellent amine resistance, resistance to aggressive aqueous media, superior overall chemical resistance, excellent compression set resistance and an upper service temperature of 300°C. Kalrez® 8775 may be a suitable replacement for Kalrez® 1050UP in wet chemistry applications. For additional information on Kalrez® 8775 in semicon industry applications, please contact a Kalrez® Technical Service & Development Engineer who can review and evaluate your specific application and needs in more detail.

### Product information

Maximum Service Temperature	572 °F
Lowest Service Temperature	-4 °F

### Typical mechanical properties

Shore A hardness	80 -	ASTM D 2240
Modulus at 100% elongation	1450 psi	ASTM D 412
Tensile Strength	2480 psi	ASTM D 412
Elongation at break	125 %	ASTM D 412
Compression Set, 70h at 204°C, O-ring (AS568-214)	10 %	ASTM D 1414

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.